

**DIAMOND AQUA EPOXY PRIMER (WATER BASED EPOXY)****PRODUCT DESCRIPTION:**

DIAMOND Aqua Epoxy is two components, water based primer, has been specifically developed for various surfaces. It is suitable for application on moist, damp and wet flooring surfaces. It is also recommended for metal surface as a general purpose interior application.

RECOMMENDED USES:

As a primer on various surfaces, such as wood, wall, cementations materials, primer for metal surfaces. Also suitable for moist, damp and wet areas

TECHNICAL DATA

COLOUR, DRY FILM	Pastel
FINISH, DRY FILM	Smooth / Matt
VOLUME SOLIDS (ASTM D2697)	45 ± 2%
SPECIFIC GRAVITY	1.30 ± 0.05
THEORETICAL SPREADING	11 – 9 M ² /LTR
RECOMMENDED DFT (DRYFILM)	40 – 50 Microns/Coat
RECOMMENDED WFT (WETFILM)	90 – 110 Microns/Coat
FLASH POINT	Water Base

DRYING TIME

Drying time @ 30°C (Temperature, humidity, air movement, film thickness and number of coats all affect the drying time.)	
TOUCH DRY	1 hour
DRY TO RECOAT	4 – 6 hours
FULLY CURED	7 days

ADVANTAGES

DIAMOND AQUA EPOXYPRIMER	Water based, easy to apply. Suitable for application on moist,damp and wet areas. Excellent adhesion on many surfaces.
---------------------------------	--

APPLICATION INSTRUCTION

SURFACE PREPARATION	Before application, the surface should be sound, clean and free From oil, grease, loose particles, dust, etc. Application can bedone by the recommended application methods.
----------------------------	---

**APPLICATION DATA**

APPLICATION METHOD	Brush, Roller, Spray
CLEANING/THINNING	Water
THINNER (VOLUME)	5%, if required
CONV. SPRAY REQUIREMENTS	Possible
AIRLESS SPRAY REQUIREMENTS	Pressure : 2100 psi
NOZZLE SIZE	0.0018" – 0.0020"
MIXING RATIO (BY VOLUME)	(Base : Hardener) 4:1 (Mix thoroughly before use)
POT LIFE @ 30°C (100 ml)	2 hours

SYSTEM

RECOMMENDED SYSTEM To be applied on prepared surface.	<u>System – 1</u>	
	DIAMOND Aqua Epoxy Primer	: 1 coat
	DIAMOND Aqua Epoxy Topcoat	: 2 coats
	<u>System – 2</u>	
	DIAMOND Aqua Epoxy Primer	: 1 coat
	DIAMOND Aqua Polyurethane	: 2 coats

DIAMOND/INTERDIAMOND TEST CERTIFICATES

Sr.NO	Test Description	Test Reference	Compliance
1	VOC	ISO 11890 – 2 USEPA 24	Local Regulatory Requirements
2	Resistance to Growth of Mold	ASTM D 3273 – 12	

ADDITIONAL DATA

SHELF LIFE @ 30°C	6 months, in original sealed container, with proper storage conditions.
--------------------------	---

**HEALTH & SAFETY**

SAFETY PRECAUTIONS	<p>Generally, most of the water base paints are quite safe to handle with due precautions. As a general rule, avoid skin and eyecontact by wearing overalls, gloves, goggles, and mask etc. Spillage on skin should immediately be removed by thorough washing with water and soap or suitable cleaner. Eye should be flushed with fresh water. Avoid inhalation of vapors and paint mist by wearing suitable mask. In the event of ingestion and eye contact, seek medical attention immediately. Painting must be carried out in well-ventilated area. Local safety regulations to be followed.</p>
-------------------------------	---

STORAGE & HANDLING

STORAGE	<p>Store the paint in proper storage conditions as per the local regulations. Keep the paint container in sealed condition under shed, away from direct sunlight and extreme temperatures. Do not stock paint material near to any ignition sources. Do not put back the half or unused material back in original container, containing the supplied paint, to avoid contamination. Handle with care. Stir well before use.</p>
----------------	---

Limited Guarantee: All Diamond Paints products are guaranteed for best performance; however since Diamond Paints does not control the final application of its products, nor the condition of the surfaces to which they are applied; a limited guarantee is provided. If the product does not perform as specified, Diamond Paints liability will under no circumstances exceed replacement of the product.

Disclaimer: To the best of our knowledge the information provided herein is true and accurate at the date of issuance. The company reserves the right to modify data contained herein without prior notice. Any change in data would normally be followed by issue of anew data sheet. The user should check with the nearest sales office of the company and confirm the validity of the information, priortouse of product.